

ard f.lli raccanello s.p.a. industria vernici e smalti

TECHNICAL SHEET 31

CODE 0.025	base Undercoat for wood and iron		
GENERAL PROPERTIES	 BASE is an anticorrosive filler paint for interior/exterior iron & wooden surfaces. It features excellent filling & spreading power, good adherence, sanding & surface/through drying. Its anti corrosion properties make it the ideal product for application on iron/cast iron (e.g., radiators). The mould resistant additives employed also protect wooden surfaces. 		
INSTRUCTIONS	Surface preparation:		
INSTRUCTIONS	 Woodwork: remove unsound paintwork by sanding. Stucco any imperfections (knots, joints, rivets, cracks etc.) with a synthetic stucco, or, for indoors with LITOSTUCCO 1.050.1010, adding as many times as necessary. Allow 24 or 6 hrs respectively, sand repair areas, clean and apply a coat of BASE. Allow 24 hours, sand the whole surface with fine sandpaper, clean thoroughly and, if necessary, apply a second coat of BASE. Allow 24 hours & finish with two coats of gloss enamel (Neoard 0.154., Tema 0.135., or Ardeol 0.151.) or satin-finish (Ardsilk 0.250.or Tema 0.235.). Ironwork & cast iron: remove any unsound paintwork and/or flaking metal using a wire brush and emery cloth. Clean the whole surface thoroughly & apply one or two coats of BASE. Allow 24 hrs, sand the surface with fine sandpaper, clean thoroughly and, if necessary, apply a second coat of BASE. Allow 24 hrs, sand the surface with fine sandpaper, clean thoroughly and, if necessary, apply a second coat of BASE. Apply the finishing enamel after 24 hrs. 		
	Application:		
	Apply BASE as follows:		
	 Brush: stir well, thin at 6-8% in volume with Diluente ARD 0.970.0030 & apply in thin coats. Allow at least 12 hours between coats. Compressed air spraying: use 8% (max) in volume of Diluente ARD 0.976.0040 & appropriate apparatuses. Allow at least 12 hours between coats. To avoid <i>removal</i>, never recoat BASE with products thinned using nitre based diluents. BASE can be tinted using ARD's glossy/silky alkyd enamels or with universal COLORATUTTO colorants 0.951. 		

- During application, especially when spraying, ensure the room is aired correctly.
- Wash equipment with the ARD 0.970.0030 thinner immediately after use.
- The product is flammable. Use in compliance with the current Health & Safety Regulations. Dispose of spent material/containers according to the same.

Refer to the PSDS for further information.

SPECIFIC WEIGHT 1415 ± 50 g/			TECHNICAL PROPERTIES		
43 ± 3s DIN Cup n° 6	4	VISCOSITY AT 20°C			
50-52%		SOLID CONTENT BY VOLUME			
matt		APPEARANCE OF FILM			
white		Colour			
after min. 12 hrs		SANDING			
2 hrs	DUST FREE				
3-4 hrs	TOUCH DRY	DRYING AT 20°C			
48 hours	THROUGH DRYING				
+39° C		FLASH POINT			

YIELD 1 coat (40 micron thick) implies a coverage of approximately 11 m²/l. Said thickness can be achieved with 1 coat using a brush or compressed air spraying.

TENDER WOOD & IRON UNDERCOAT

SPECIFICATION ITEM Anticorrosive fungicidal matt paint with excellent filling properties for wood & iron. Application of 1 or 2 coats on pretreated surfaces, of anticorrosive filling undercoat for wood & iron type BASE 0.025.1010 for interiors/exteriors, with a minimum consumption of 0.10 l/m².

€/m²

The data herein were true at the time of Quality Control and refer to standardized environmental conditions. The same are to be considered as a guide. Revision 2012/07



ard • f.lli raccanello s.p.a. • industria vernici e smalti 35129 PADOVA – Zona Ind.le Nord 1^a Strada, 13 – Tel. 049.8060000 (5 linee) Fax 049.773749 – www.ard-raccanello.it - E-mail: ardspa@ard-raccanello.it