



ard f.lli raccanello s.p.a. industria vernici e smalti

TECHNICAL SHEET **40**

CODE 1.050.1010

litostucco

Rapid hydro-stucco for wood & plasterwork

GENERAL PROPERTIES

A soft spatulable stucco based on polymers in aqueous dispersion which offers good filling power, quick drying, effortless ease of sanding & reduced shrinkage.

LITOSTUCCO is the perfect product for the refinishing & filling of interior walls & the preparation of interior wooden substrates.

INSTRUCTIONS

Substrate preparation:

Interior two-coat plaster work/gypsum walls: thoroughly clean the areas to be stuccoed (knots, joints, rivets etc.), dampen & apply LITOSTUCCO adding as many times as necessary. Allow 6 hrs fill, sand the stuccowork, clean accurately & seal the whole surface with a hand of ISOLEX W, ARDFIX or BIANCOFIX. Allow 4 hrs & finish with an ARD emulsion paint (IDROPAINT - AEDILIA - TRASPIRA etc.).

Wooden surfaces: clean and level any imperfections (knots, joints, fissures etc.) with LITOSTUCCO. Allow 6 hrs sand the stuccowork, clean & apply 1 or 2 hands of ARDEOLITE 0.022.1010 or BASE 0.025.1010. Allow 12 hrs & finish with two layers of glossy (NEOARD 0.154. - ARDEOL 0.151) or satiny enamel (ARD SILK 0.250).

If after sanding LITOSTUCCO, water-dilutable products are to be used, apply two layers of TEMA pittura opaca di fondo 0.028.1010. Allow 6 hrs, sand the surface & apply two layers of TEMA SMALTO IDRODILUIBILE (glossy or satiny).

Application:

Amalgamate LITOSTUCCO using a spatula & thinning if necessary with small amounts of water. Apply by filling, as many times as necessary, in thin layers at 1 hr intervals. The recommended thickness is 0,5 mm per layer. Allow 6 hrs & sand.

- Do not apply under direct sunlight or at ambient/substrate temperature below + 5°C. or above + 35°C.
- Wash equipment immediately after use with water.
- Store in a cool place under frost proof conditions.

- Use products in compliance with current Hygiene & Safety Regulations. Dispose of spent material/containers according to the same.

Refer to the PSDS for further details.

TECHNICAL PROPERTIES

SPECIFIC WEIGHT	1920 ± 50 g/l	
COLOUR	White	
SANDING	After 6 hrs	
DRYING AT 20 °C	TOUCH DRYING	1 hr
	THROUGH DRYING	8 hrs

YIELD

A 0,5 mm dry layer of LITOSTUCCO implies a yield of 1 m²/kg.

SPECIFICATIONS

RAPID HYRO-STUCCO FOR WOOD & PLASTER

Application on cement/lime plaster & wood, of spatulable water based filling stucco based on synthetic resins in aqueous dispersion & inert fillers type LITOSTUCCO with an approx min consumption of 1 kg/m² per 0.5 mm thickness.

€/m².

The data herein were correct at the time of Quality Control and refer to standardized environmental conditions. The same are to be considered as a guide.
Revision 2014/10



ard · f.lli raccanello s.p.a. · industria vernici e smalti

35129 PADOVA – Zona Ind.le Nord 1^a Strada, 13 – Tel. 049.8060000 (5 linee)

Fax 049.773749 – www.ard-raccanello.it - E-mail: ardspa@ard-raccanello.it