



# ard f.lli raccanello s.p.a. industria vernici e smalti

TECHNICAL SHEET 82

CODE 1.637

## spachtel rustico 1,2 mm

Acrylic plaster

### GENERAL PROPERTIES

SPACHTEL RUSTICO 1,2 mm is a fibre-reinforced plastic coating for interiors & exteriors. The product offers an optimum resistance to alkali/atmospheric agents, remarkable elasticity, adherence, low dirt pick-up, excellent application & workability. The excellent alkali resistance and lightfast pigments (UV rays) guarantee the solidity of the hues even on walls exposed to strong sunlight & weather extremes.

SPACHTEL RUSTICO 1,2 mm is suitable for the protection of urban buildings in two coat plaster work, cement mortar renders, gypsum plaster for interiors & smooth compact prefabricated concrete structures.

### INSTRUCTIONS

#### Substrate preparation:

- Bare walls: ensure the substrate has weathered for at least 28 days. Clean thoroughly, removing dust, filth, & any unsound parts. Ensure the wall is perfectly dry and apply a hand of ISOLEX W, ISOLEX or ARDFIX suitably thinned (1 part of product in 8 parts of water). Allow 12 or 4 hrs respectively; level large imperfections with ARDPLAN AS or ARDPLAN BS. Apply a layer of RASANTE A PENNELLO 0.084.1010 on smooth &/or poor absorbing surfaces in order to achieve the desired result. Allow at least 6 hrs and apply SPACHTEL RUSTICO 1,2 mm.
- Unsound painted surfaces: remove any unsound paintwork and efflorescence. Treat mould with ARDSAN RISANANTE MURALE 0.916.. Clean thoroughly, ensure the surface is perfectly dry & fix with a coat of ISOLEX W or ISOLEX. Allow 12 hrs & stucco the large imperfections with ARDPLAN AS or ARDPLAN BS & apply SPACHTEL RUSTICO 1.2 mm.
- Surfaces with unsound plastic coatings/embossed plaster: remove any unsound paintwork & efflorescence. Treat mould with ARDSAN RISANANTE MURALE. Clean thoroughly, ensure the wall is perfectly dry and seal the whole surface with a layer of ISOLEX W or ISOLEX. Allow 12 hrs, accurately level the whole surface and apply SPACHTEL RUSTICO 1,2 mm.
- When finishing products with limited covering power are employed we suggest using PRIMER RIEMPITIVO COPRENTE 0.075 (refer to the formulary for shades).

## Application:

- SPACHTEL RUSTICO 1,2 mm can be used neat. Stir well; apply only one coat with a steel or plastic trowel. Level the surface with a trowel before the product forms a surface film.
- Do not apply at ambient/substrate temperatures below + 5°C or above 35°C & R H above 75%. Avoid applying during cold & damp periods, in direct sunlight or strong wind.
- Outdoor surfaces must be protected against rain until perfectly dry (normally after 48 hrs at 20°C).
- Wash equipment immediately after use with water.
- Store in cool, frost proof premises.
- Use products from the same batch, *if* different batches are used, stir accurately to avoid differences in shades.
- When applying on extensive surfaces apply “wet on wet” to avoid patches.
- Walls with efflorescence or subject to rising damp must be restored before application in order to guarantee adherence.
- Use in compliance with the current Health & Safety Regulations. Dispose of spent material/containers according to the same.
- Refer to the PSDS for further details.
- SPACHTEL RUSTICO 1,2 mm code 1.637 is compatible with the 16COLOURS & WIZARD tinting systems.

## TECHNICAL PROPERTIES

NATURE OF BINDER	Acrylic polymers		
COLOUR	White & tinting system hues		
MASS VOLUME	1700 - 1800 g/l		
DYNAMIC VISCOSITY	150.000 - 200.000 cP		
UV RESISTANCE	Sup. 3 <sup>rd</sup> grade Grey scale		
ALKALI RESISTANCE	No structural/chromatic variation		
DRYING AT 20°C	TOUCH DRY		4 hrs
	THROUGH DRYING		48 hrs
PERMEABILITY (WATER VAPOUR)	EN ISO 7783-1 & 2	S <sub>d</sub>	0,323 m
		Class	V <sub>2</sub> (average)
CAPILLARY ABSORPTION & WATER PERMEABILITY	EN1062-3	W	0,052 kg/m <sup>2</sup> √t
		Class	W <sub>3</sub> (low)
ADHESION FOR DIRECT TRACTION	EN 1542	RESULT	Complies (adhesion ≥ 0,3 Mpa)
DURABILITY	EN 13687-3	RESULT	Complies (adhesion ≥ 0,3 Mpa)
THERMAL CONDUCTIVITY	EN 1745	λ10DRY [W/MK]	1,092
FLASH POINT	EN 13501-1		Class C
HAZARDOUS SUBSTANCES		RESULT	Complies

*In compliance with the UNI EN 15824 CE Marking*

---

## YIELD

Once dry the coating is about 1,2 mm thick. Coverage depends on the substrate but is approx. 0,45 m<sup>2</sup>/kg.

Said yield refers to smooth substrates with medium absorption; we recommend testing on the specific substrate.

---

**TENDER  
SPECIFICATION ITEM**

**ACRYLIC PLASTER**

Trowel application on treated surfaces of a plastic fibre-reinforced coating based on acrylic copolymers in aqueous dispersion, coloured pigments & mineral fillers of calibrated granulometry like SPACHTEL RUSTICO 1,2 mm which after drying produces a 1,2 mm thickness & minimum consumption of 2,2 kg/m<sup>2</sup>.

€/m<sup>2</sup>

---

*The data herein were correct at the time of Quality Control & refer to standardized environmental conditions. The same are to be considered as a guide.  
Revision 2015/06*



**ard · f.lli raccanello s.p.a. · industria vernici e smalti**

35129 PADOVA – Zona Ind.le Nord 1<sup>a</sup> Strada, 13 – Tel. 049.8060000 (5 linee)  
Fax 049.773749 – [www.ard-raccanello.it](http://www.ard-raccanello.it) - E-mail: [ardspa@ard-raccanello.it](mailto:ardspa@ard-raccanello.it)