

ard f.lli raccanello s.p.a. industria vernici e smalti

TECHNICAL SHEET 168

CODE 2.142.

ard spray zinco

Acrylic enamel spray

GENERAL PROPERTIES

ARD SPRAY ZINCO is a highly anti-corrosive cold zincking based on acrylic resins & 95% zinc powder.

ARD SPRAY ZINCO is suitable for the anticorrosive protection of metal surfaces in general (coverings, conduits, tanks & rainspouts) & interior/exterior galvanised sheet iron.

ARD SPRAY ZINCO does not contain any dangerous substances such as chrome, lead or chlorine-fluorine derivatives.

INSTRUCTIONS

Substrate preparation:

 Degrease with thinner Diluente ARD 0.972.0042. Remove any flaky metal & rust with a wire brush & emery cloth. Clean thoroughly, apply two coats of ARD SPRAY allowing a few minutes between the coats. Ensure the surface is "cold" before painting. Do not apply near incandescent surfaces or combustive sources.

Application:

- Shake well (at least 1 min.) before using.
- If the temperature is below 15 °C warm with lukewarm water.
- A good result can be obtained by applying a number of very thin layers at intervals of a few minutes. Spray upright at a distance of about 25-30 cm.
- ARD SPRAY ZINCO can be recoated with the ARD SPRAY line of products. Do not overlay using bicomponent products.
- Ensure premises are "aired" sufficiently. Avoid inhaling propellant vapours.
- Any residues can be conserved by placing the can upside down & pressing the valve for a moment.
- Store the cans following the usual precautions; keep out of the reach of children and away from heat.
- Do not dispose until completely empty.

TECHNICAL PROPERTIES

	DUST FREE	10 mins
DRYING AT 20 °C	TOUCH DRY	30 mins
	THROUGH DRYING	24 hrs

YIELD

If applied correctly, one can covers a $2\ m^2$ surface.

TENDER SPECIFICATION ITEM

ACRYLIC ENAMEL SPRAY

Application on pretreated iron or zinc surfaces of two layers of anticorrosive paint spray based on acrylic resins resistant & zinc powder type ARD SPRAY ZINCO with a min. consumption of (1 can) approx 2 $\rm m^2$.

€/m²

The data herein were correct at the time of Quality Control and refer to standardized environmental conditions. The same are to be considered as a guide.

Revision 2007/11



ard • f.lli raccanello s.p.a. • industria vernici e smalti 35129 PADOVA – Zona Ind.le Nord 1ª Strada, 13 – Tel. 049.8060000 (5 linee) Fax 049.773749 – www.ard-raccanello.it - E-mail: ardspa@ard-raccanello.it