



ard f.lli raccanello s.p.a. industria vernici e smalti

TECHNICAL SHEET **211**

CODE 0.516

siliard paint

Siloxanic algae resistant exterior paint

GENERAL PROPERTIES

SILIARD PAINT is formulated using advanced technologies based on nanoparticles & siliceous binders in aqueous dispersion. These features lend a remarkable water vapour permeability, water-repellence & low water absorption.

SILIARD PAINT does not “film”, it produces a porous/transpiring matt coat which adheres perfectly to both mineral substrates & old mineral/synthetic paintwork.

SILIARD PAINT offers an outstanding resistance to weather extremes, low dirt pick-up & inhibits formation of micro-organisms such as mould & algae.

SILIARD PAINT is specific for the protection & decoration of listed buildings, external plaster, transpiring restoration plaster & porous materials in general which require optimum protection & low water vapour diffusion resistance.

INSTRUCTIONS

Surface preparation:

- Bare walls with light cement mortar plaster: ensure the substrate has weathered for at least 28 days, clean thoroughly, removing dust/ filth & unsound paintwork. If necessary stucco with a suitable restoration mortar. Ensure the wall is perfectly dry and apply a coat of SILIARD PRIMER W 0.077. thinned at 50-100% in water volume. Apply at least 150 ml/m² (thinned) allow at least 24 hours & apply SILIARD PAINT.
- Chalky substrates & porous walls/bricks: apply a layer of SILIARD PRIMER 0.082. (ready siloxanic consolidating impregnating agent). Apply at least 200 ml/m² (thinned); allow 24 hours and apply SILIARD PAINT.
- Walls with mineral lime wash or silicate-based paintwork: remove any unsound paintwork & efflorescence. Clean thoroughly, remove dust & filth. Ensure the substrate is dry and apply a layer of SILIARD PRIMER S 0.082. (ready siloxanic consolidating impregnating agent). Allow at least 24 hours & apply SILIARD PAINT.
- Walls with synthetic paintwork: remove any unsound paintwork. Use SILIARD PRIMER S 0.082. to treat bare plaster & repair areas. Allow 24 hrs & apply SILIARD PAINT.

- Walls with efflorescence or subject to rising damp must be restored before application in order to guarantee adherence.
- We recommend pretreating mould, algae or moss with ARDSAN RISANANTE MURALE 0.916..

Application:

Apply SILIARD PAINT as follows:

- Brush: stir well, thin at 30-35% in water volume & apply using about 80-90 ml/m² per layer. Allow at least 12 hours and apply the second layer.
- Wool or synthetic fibre roller: thin at 25-30% in water volume and apply the product in one go, wet on wet. Allow at least 12 hours and apply the second coat.
- Do not apply SILIARD PAINT at ambient or substrate temperature below + 5°C or above + 30°C.
- After application, exterior walls must be protected against rain, frost, fog & dew for at least 48 hours. The drying times indicated in the Technical Properties refer to a temperature of +20°C & 65% R.H. Consequently, drying may take much longer when temperatures are lower and humidity is higher. This, in turn, lengthens recoating/protection times.
- When different batches are used, we recommend mixing the products thoroughly in order to avoid differences in shades.
- SILIARD PAINT is compatible with the 16 COLOURS tinting systems.
- Store in cool, frost free premises.
- Wash equipment immediately after use with water.
- Use in compliance with current Health & Safety Regulations. Dispose of spent material/containers according to the same.

Refer to the PSDS for further information.

TECHNICAL PROPERTIES

SPECIFIC WEIGHT		1520 ± 50 g/l
VISCOSITY AT 20°C		14.000 ± 2.000 cps
NATURE OF BINDER		Acrylic-siloxanic
DRYING AT 20 °C	TOUCH DRYING	1 hr
	THROUGH DRYING	48 hrs
COATABILITY		min. 12 hours
LIQUID WATER TRANSMISSION	UNI EN 1062-3	w= 0,0.3 kg/m² √t
LIQUID WATER TRANSMISSION	UNI EN 1062-1	Class W3
WATER VAPOUR PERMEABILITY	UNI EN 7783-2	Sd = 0,02 m
WATER VAPOUR PERMEABILITY	UNI EN 1062-1	Class 3

YIELD

The two-coat painting cycle implies a coverage of about 6 m²/l of SILIARD PAINT. It is best to determine the same by testing on the specific substrate.

**TENDER
SPECIFICATION ITEM**

SILOXANIC ALGAE RESISTANT EXTERIOR PAINT

Application on pretreated surfaces of two layers of paint for exteriors based on acrylic-siloxanic resins in aqueous dispersion & lightfast pigments with capillary water absorption in compliance with the EN 1062-3 regulation $W \leq 0,1 \text{ Kg/m}^2 \cdot \text{h}^{0,5}$, water vapour permeability in compliance with EN ISO 7783-2 $S_D \leq 0,14$ metres, type SILIARD PAINT, with a minimum consumption of 0.17 l/m².

€/m²

The data herein were correct at the time of Quality Control and refer to standardized environmental conditions. The same are to be considered as a guide.

Revision 2014/11



ard - f.lli raccanello s.p.a. - industria vernici e smalti

35129 PADOVA – Zona Ind.le Nord 1^a Strada, 13 – Tel. 049.8060000 (5 linee)
Fax 049.773749 – www.ard-raccanello.it - E-mail: ardspa@ard-raccanello.it